



Distributed by KPR Adcor Inc.
USA & Canada Toll Free: 1-866-577-2326
Phone: 1-905-628-3232 Fax: 1-866-908-6992
Web: Corrosionvci.com Email: kpr@corrosionvci.com

Technical Data



40PCF FERRO-PAK

PRODUCT DESCRIPTION

40 lb. poly coated kraft; paper side saturated with nitrite-free chemical compound which provides protection of ferrous metals.

TYPICAL PHYSICAL TEST RESULTS

	<u>Typical Values</u>	<u>Tappi Test Method</u>
Basis Weight, Lbs/R (24 X 36 - 500)	52.5	T-410
Caliper, Mils.	5.7	T-411
Tearing Strength, Elmendorf, gms.		T-414
Machine Direction	104	
Cross Machine Direction	117	
Bursting Strength, (psi)	37	T-403
Tensile Strength, (lbs/in.)		T-404
Machine Direction	25	
Cross Machine Direction	14	

These results are typical values and are not to be construed as specifications. If specifications are required, please discuss with your sales representative.

INHIBITOR PROTECTION

Metal

Aluminum
Steel, AISI 1010
Cast Iron
Brass, Red or White
Bronze, including Naval
Copper
Cadmium or Cadmium Plated

Protection

Not Recommended
Protection
Protection
Not Recommended
Testing Required
Not Recommended
Testing Required

Metal

Stainless Steel, All Grades
 Galvanized, hot dipped or electroplated
 Chromium or Chromium Plated
 Nickel or Nickel Plated
 Silver or Silver Plated
 Magnesium
 Lead or solder
 Tin or tinplate
 Zinc or White Metal

Protection

Protection
 Not Recommended
 Testing Required
 Testing Required
 Not Recommended
 Not Recommended
 Not Recommended
 Protection
 Not Recommended

“Testing Required” indicates product will usually protect this metal type, however, for best results Daubert Cromwell testing before use. Daubert Cromwell always recommends corrosion testing of customer-provided samples of metals and all chemicals to better confirm these statements.

SHELF LIFE

36 months from date of original shipping. This shelf life statement is only valid for product stored in the original shipping container used by Daubert Cromwell and not in high humidity and not at high temperatures. Storage outside these conditions voids this statement.

TK: 12/9/04

Rev. 8/05, JB, company name, address, phone and fax only.



The data, statements and recommendations in this product information sheet are based on testing, research and other development work, which has been carefully conducted by us, and we believe such data, statements and recommendations will serve as reliable guidelines. Physical properties shown above represent typical values and are not intended for use in writing specifications. However, this product is subject to numerous uses under varying conditions over which we have no control, and accordingly, we do NOT warrant that this product is suitable for any particular use. Users are advised to test the product in advance to make certain it is suitable for their particular production conditions and use.

WARRANTY – All products manufactured by us are warranted to be first class material and free from defects in material and workmanship. Liability under this warranty is limited to the net purchase price of any such products proven defective or, at our option, to the repair or replacement of said products upon their return to us transportation prepaid. All claims on defective products must be made in writing within 30 days after the receipt of such products in your plant and prior to further processing or combining with other material and products.

WE MAKE NO WARRANTY, EXPRESS OR IMPLIED, AS TO THE SUITABILITY OF ANY OF OUR PRODUCTS FOR ANY PARTICULAR USE, AND WE SHALL NOT BE SUBJECT TO LIABILITY FROM ANY DAMAGES RESULTING FROM THEIR USE IN OPERATIONS NOT UNDER OUR DIRECT CONTROL.

THIS WARRANTY IS EXCLUSIVE OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, AND NO REPRESENTATIVE OF OURS OR ANY OTHER PERSON IS AUTHORIZED TO ASSUME FOR US ANY OTHER LIABILITY IN CONNECTION WITH THE SALE OF OUR PRODUCTS.