

DAUBERT VCI® NOX-RUST® LIQUID
5300 (Nox-Rust 503 L.S.)
LOW VOC, SOLVENT TYPE, COLD APPLIED RUST PREVENTIVE
(SOFT, WATER DISPLACING FILM)

Nox-Rust 5300 is designed for use where water or saline solution must be displaced from corrodible surfaces and the corrosion prevented or arrested. It can be used to protect interior surfaces of machinery, instruments or material under cover for limited periods, and to protect critical bare steel or phosphated surfaces for extended periods when packaged with satisfactory barrier materials. Available in 55-gallon drums and 5-gallon pails.

Nox-Rust 5300 can be removed by conventional cleaning procedures, with petroleum solvents, and alkali or emulsion cleaners. It is completely miscible with lubricating oils, which, in some cases, eliminates the need for removal of coating.

PHYSICAL PROPERTIES (Typical Values, Not Specifications)

Application	Dipping, spraying or brushing down to 40°F.
Film Description	Brown, oily
Thickness, mils	0.4 (.010 mm)
Setting Time, hours	1/2 - 3/4
Flash Point	105°F. (40°C)
Pounds per Gallon	7.0
Specific Gravity	0.84
Volatile Organic Compounds (lbs/gal)	3.5

PROTECTIVE PROPERTIES (Typical Values)

Outdoor Storage, Min.	Not recommended
Outdoor Storage, covered	6 months

ACCELERATED TESTS

100% RH @ 120°F. (49°C) min.	30 days
------------------------------	---------

3/15/04

The data, statements and recommendations in this product information sheet are based on testing, research and other development work, which has been carefully conducted by us, and we believe such data, statements and recommendations will serve as reliable guidelines. Physical properties shown above represent typical values and are not intended for use in writing specifications. However, this product is subject to numerous uses under varying conditions over which we have no control, and accordingly, we do NOT warrant that this product is suitable for any particular use. Users are advised to test the product in advance to make certain it is suitable for their particular production conditions and use.

WARRANTY – All products manufactured by us are warranted to be first class material and free from defects in material and workmanship. Liability under this warranty is limited to the net purchase price of any such products proven defective or, at our option, to the repair or replacement of said products upon their return to us transportation prepaid. All claims on defective products must be made in writing within 30 days after the receipt of such products in your plant and prior to further processing or combining with other material and products.

WE MAKE NO WARRANTY, EXPRESS OR IMPLIED, AS TO THE SUITABILITY OF ANY OF OUR PRODUCTS FOR ANY PARTICULAR USE, AND WE SHALL NOT BE SUBJECT TO LIABILITY FROM ANY DAMAGES RESULTING FROM THEIR USE IN OPERATIONS NOT UNDER OUR DIRECT CONTROL.

THIS WARRANTY IS EXCLUSIVE OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, AND NO REPRESENTATIVE OF OURS OR ANY OTHER PERSON IS AUTHORIZED TO ASSUME FOR US ANY OTHER LIABILITY IN CONNECTION WITH THE SALE OF OUR PRODUCTS.

**PRODUCT
INFORMATION****NOX-RUST® 503LS****Description**

NOX-RUST® 503 LS is for use where water or saline solution must be displaced from corrodible surfaces and the corrosion prevented or arrested. For protection of interior surfaces of machinery, instruments or material under cover for limited periods. For protection of critical bare steel or phosphated

surfaces for extended periods when packaged with satisfactory barrier materials. Nox-Rust® 503LS is a solvent type, cold application, rust preventive, low voc soft film that meets Specification Mil-C-16173E, Grade 3, Class II.

PHYSICAL PROPERTIES**TYPICAL VALUES**

Application	Dipping, spraying or brushing down to 40° F
Film Description	Brown, oily
Thickness, mils	0.4 (0.010 mm)
Setting Time, hours	1/2 - 3/4
Flash Point	105°F (40°C)
Pounds per Gallon	7.0
Specific Gravity	0.84
Volitile Organic Compounds (lbs/gal)	3.5

Protective Qualities (Typical Values)

Outdoor Storage, Min.	Not recommended
Outdoor Storage, covered	6 months

Accelerated Tests

100% RH @ 120°F (49°C) min.	30 days
-----------------------------	---------

NOX-RUST® 503 LS can be removed by conventional cleaning procedures or petroleum solvents, alkali or emulsion cleaners. The product is completely miscible with lubricating oils which, in some cases, eliminates the need for removal of coating.

Surface Preparation

The maximum performance of NOX-RUST® 503LS can be achieved only when the metal surfaces to be protected are clean, dry and free of rust, oil and mill scale. Daubert Chemical Company recommends that the metal substrate temperature be 50-95°F (10-35°C) at the time of product application.

Application

NOX-RUST® 503LS is formulated to be used as supplied. Ensure uniform consistency prior to use. Continued stirring is generally not required. If the product thickens due to cold storage or loss of solvent during use, contact Daubert Chemical Company. DO NOT THIN NOX-RUST® 503LS. Incorrect thinning will affect film build, dry time and product performance. Daubert Chemical Company recommends that the ambient and product temperature be 50 - 95° F (10 - 35°C) at time of application. NOX-RUST® 503LS can be spray or dip applied.

Removal

NOX-RUST® 503LS can be removed with a solvent borne thinner, vapor degreasing, hot alkaline wash, or low-pressure steam. NOX-RUST® 503LS can be removed from fabrics by normal dry cleaning procedures. Avoid the use of chlorinated or highly aromatic solvents when removing from painted surfaces, as these solvents may adversely affect paint.

Storage

Store NOX-RUST® 503LS at temperatures between 50-95°F (10-35°C). Mild agitation is recommended prior to use.

Caution

Adequate ventilation is required for cure and to ensure against formation of a combustible liquid. THE PARTIALLY CURED FILM SHOULD NOT BE EXPOSED TO IGNITION SOURCES SUCH AS FLARES, FLAMES, SPARKS, EXCESSIVE HEAT, OR TORCHES. Refer to Daubert's Material Safety Data Sheet for additional handling and first aid information.

Note:

The addition of any product over or under this coating is not recommended. The use of additional coatings could result in chemical incompatibility, thus adversely affecting the performance of this coating as stated in the lab data section. If a product other than Daubert Chemical Company's recommended product is required, written authorization must be obtained from Daubert Chemical Company.

4/30/04:kp

CAUTION: The data, statements and recommendations set forth in this product information sheet are based on testing, research and other development work which has been carefully conducted by us, and we believe such data, statements and recommendations will serve as reliable guidelines. However, this product is subject to numerous uses under varying conditions over which we have no control, and accordingly, we do NOT warrant that this product is suitable for any particular use. Users are advised to test the product in advance to make certain it is suitable for their particular production conditions and particular use or uses.

WARRANTY: Daubert Chemical Company, Inc. ("Daubert") warrants all products manufactured by it to be free from defects in material and workmanship. DAUBERT MAKES NO OTHER WARRANTIES, WHETHER, EXPRESSED OR IMPLIED, WITH RESPECT TO SUCH PRODUCTS, AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND IMPLIED WARRANTIES ARISING FROM A COURSE OF DEALING OR USAGE OF TRADE, ARE DISCLAIMED BY DAUBERT. All claims hereunder must be made in writing within 30 days after receipt of the products at the buyer's plant and prior to further processing the products or combining them with other materials or products. Daubert's liability, whether under this warranty or in contract, tort, negligence or otherwise, is limited to the return of the net purchase price paid for any products proven defective or, at Daubert's option, to the repair or replacement of said products upon their return, transportation prepaid, to Daubert. THE REMEDY HEREBY PROVIDED SHALL BE THE EXCLUSIVE AND SOLE REMEDY OF THE BUYER, AND UNDER NO CIRCUMSTANCES SHALL DAUBERT BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES. No Daubert representative or other person is authorized to change this warranty in any way or to assume for Daubert any other liability in connection with the sale or use of its products.

REFER TO MATERIAL SAFETY DATA SHEET FOR HEALTH AND SAFETY INFORMATION.

DAUBERT
CHEMICAL COMPANY, INC.

4700 S. Central Ave., Chicago, IL 60638 • (708) 496-7350