

# KPR ADCOR INC.

**'We Stop Rust' TM**

**Technical Data**

Toll Free: (866) 577-2326  
Telephone: (905) 628-3232  
Fax: (905) 628-2529

[www.corrosionvci.com](http://www.corrosionvci.com)  
email: [kpr@corrosionvci.com](mailto:kpr@corrosionvci.com)

## LUDLOW FILM FR 2175B

**Construction:** 90ga Polypropylene/15# LDPE/.000285 Foil/40# LDPE

**Specification:** Mil-B-131, Type 1, Class 1

**QPL:** Qualified product under test number NAVAIRDEVCEEN LTR 6061  
SER 3684 dated 19 April 1983

**Stock:** 36" and 48" wide roll stock. Special widths available upon request.

### PHYSICAL PROPERTIES

<u>Property</u>	<u>Test Method</u>	<u>Unit of Measure</u>	<u>Typical Values</u>
Tensile:	ASTM-D-882	Lbs at break	
MD			34.0
XMD			29.0
Tear:	ASTM-689	Grams	
MD			64.0
XMD			64.0
MVTR:	Mocon	Gms/100 In <sup>2</sup> /24 Hrs	
Flat			.0006
O2TR:	Mocon	cc/100 In <sup>2</sup> /24 Hrs	.0006
Puncture:	Fed TM 2065	Lbs.	15.0
Seal Strength:	ASTM-D-882	Lbs/In	10.0
@375F; 26psi; 1 sec			
Caliper:		Mils	5.0
Yield:		SI/ Lb	5400

Custom made bags fabricated & distributed by:

[www.CorrosionVCI.com](http://www.CorrosionVCI.com)

**Kpr Adcor Inc**

Email: [kpr@corrosionvci.com](mailto:kpr@corrosionvci.com)

Toll Free: 1-866-577-2326 Phone: 905-628-3232

Fax: 905-628-2529