

Distributed by KPR Adcor Inc.
www.corrosionvci.comToll free: 1-866-577-2626
Telephone: 905-628-3232
Facsimile: 905-628-2529Web site: www.corrosionvci.com
Email: kpr@corrosionvci.com**UNIWRAP® A****PC50A Scrim****PRODUCT DESCRIPTION**

A 50 lb./ream (81 g/m²) natural kraft coated with 1 mil of white low-density polyethylene reinforced with tridirectional scrim. The paper is saturated with Daubert VCI's multi-metal Uniwrap® A volatile corrosion inhibitor (VCI) formulation. Designed for protecting ferrous/non-ferrous metals combinations, PC50A Scrim is specially useful as sheeting material for interleaving between pallets and heavy steel rolls. It can also be used when the application requires higher strength and barrier properties than standard VCI coated kraft paper. For even higher strength, request UW94A.

PHYSICAL PROPERTIESCoating Deposition: 7.5 lb./ream (12 g/m²) minimum

<u>Property</u>	<u>Units</u>	<u>Typical Value</u>		<u>Test Method</u>
Basis Weight	lb./ream (g/m ²)	80 (130)		T-410
Caliper	mil (µm)	12 (305)		T-411
Mullen Burst	psi (kPa)	52 (359)		T-403
		<u>MD</u>	<u>CD</u>	<u>Test Method</u>
Elmendorf Tear	g/ply (mN/ply)	289 (2835)	299 (2933)	T-414
Tensile Strength	lb./in (kN/m)	42 (7.36)	14 (2.45)	T-494

INHIBITOR PROTECTION

Classified as six months protection when stored outside and properly protected from moisture and other environmental elements; 24 months minimum, inside dry storage.

Metal**Corrosion Protection**

Mild Carbon Steel, Cast Iron

Provides protection in contact and vapor phases.

Aluminum

Passive. Good protection in contact phase. Test for compatibility.

UNIWRAP[®] A

PC50A Scrim

Metal

Corrosion Protection

Zinc or Zinc Galvanized Steel	Provides protection in contact and vapor phases.
Copper	Provides protection in contact and vapor phases.
Brass ¹	May protect. Test for compatibility.
Bronze	May protect. Test for compatibility.
Silver	Not recommended ⁴ . Silver Saver [®] recommended
Category A ²	May protect; Test for compatibility.
Category B ³	May protect; Test for compatibility.

- 1 Brass alloys in the "red" area containing up to 20% zinc will act like copper; brass in the "white" area containing over 20% zinc and will act like Category A metals.
- 2 Category A metals include zinc, cadmium, nickel, cadmium-plated steel, and nickel-plated steel. These are prone to contact corrosion sensitivity with inhibitor chemicals, but will be protected as shown in the vapor phase.
- 3 Category B metals include lead, antimony, babbitt alloys, solder, magnesium or magnesium alloys.
- 4 "Not recommended" does not indicate incompatibility. Compatibility testing is always recommended. Our "not recommended" rating indicates that there may be more effective Daubert VCI[®] products for these applications. Your sales representative can help recommend the optimal product for specific applications.

The data, statements and recommendations in this product information sheet are based on testing, research and other development work, which has been carefully conducted by us, and we believe such data, statements and recommendations will serve as reliable guidelines. Physical properties shown above represent typical values and are not intended for use in writing specifications. However, this product is subject to numerous uses under varying conditions over which we have no control, and accordingly, we do NOT warrant that this product is suitable for any particular use. Users are advised to test the product in advance to make certain it is suitable for their particular production conditions and use.

WARRANTY – All products manufactured by us are warranted to be first class material and free from defects in material and workmanship. Liability under this warranty is limited to the net purchase price of any such products proven defective or, at our option, to the repair or replacement of said products upon their return to us transportation prepaid. All claims on defective products must be made in writing within 30 days after the receipt of such products in your plant and prior to further processing or combining with other material and products.

WE MAKE NO WARRANTY, EXPRESS OR IMPLIED, AS TO THE SUITABILITY OF ANY OF OUR PRODUCTS FOR ANY PARTICULAR USE, AND WE SHALL NOT BE SUBJECT TO LIABILITY FROM ANY DAMAGES RESULTING FROM THEIR USE IN OPERATIONS NOT UNDER OUR DIRECT CONTROL.

THIS WARRANTY IS EXCLUSIVE OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, AND NO REPRESENTATIVE OF OURS OR ANY OTHER PERSON IS AUTHORIZED TO ASSUME FOR US ANY OTHER LIABILITY IN CONNECTION WITH THE SALE OF OUR PRODUCTS.