

Distributed by: KPR ADCOR INC. 'We Stop Rust!' TM Canada & USA Toll Free 1-866-577-2326  
Tel: 905-628-3232 Fax: 866-908-6992 Web site: www.corrosionvci.com Email: kpr@corrosionvci.com

**DAUBERT VCI® NOX-RUST® LIQUID**  
**5100 (Nox-Rust 501-LS)**  
SOLVENT TYPE, COLD APPLICATION, RUST PREVENTIVE  
(HARD FILM)

**Nox-Rust 5100** is designed to protect metals when exposed to outdoor weather conditions and for general purpose preservation, indoor or outdoor, with or without cover, for domestic and overseas shipment where a "dry to touch" film is required. Available in 55-gallon drum and 5-gallon pail quantities.

**Nox-Rust 5100** can be removed by conventional cleaning procedures or with petroleum solvents.

Nox-Rust 501 LS is on the Qualified Products List for Mil-PRF-16173 Grade 1 Class 1.

QPL 16173-93 Test Reference: Test Reference: Daubert Rpt. Reference: 4123 03R42/62

**PHYSICAL PROPERTIES (Typical Values, Not Specifications)**

Application	Dipping, spraying, or brushing
Film Description	Black, slightly tacky
Thickness, mils	2.5 (.063 mm)
Setting time, hrs	5-8
Min. Flash Point, of Compound	105°F (41°C)
Pounds per Gallon	7.34
Specific Gravity	0.88
Protective Qualities: Outdoor storage, min.	1 year
Accelerated Tests: 20% Salt Spray, min.	14 days
Weatherometer	1,200 hours

3/15/04

The data, statements and recommendations in this product information sheet are based on testing, research and other development work, which has been carefully conducted by us, and we believe such data, statements and recommendations will serve as reliable guidelines. Physical properties shown above represent typical values and are not intended for use in writing specifications. However, this product is subject to numerous uses under varying conditions over which we have no control, and accordingly, we do NOT warrant that this product is suitable for any particular use. Users are advised to test the product in advance to make certain it is suitable for their particular production conditions and use.

**WARRANTY** – All products manufactured by us are warranted to be first class material and free from defects in material and workmanship. Liability under this warranty is limited to the net purchase price of any such products proven defective or, at our option, to the repair or replacement of said products upon their return to us transportation prepaid. All claims on defective products must be made in writing within 30 days after the receipt of such products in your plant and prior to further processing or combining with other material and products.

WE MAKE NO WARRANTY, EXPRESS OR IMPLIED, AS TO THE SUITABILITY OF ANY OF OUR PRODUCTS FOR ANY PARTICULAR USE, AND WE SHALL NOT BE SUBJECT TO LIABILITY FROM ANY DAMAGES RESULTING FROM THEIR USE IN OPERATIONS NOT UNDER OUR DIRECT CONTROL.

THIS WARRANTY IS EXCLUSIVE OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, AND NO REPRESENTATIVE OF OURS OR ANY OTHER PERSON IS AUTHORIZED TO ASSUME FOR US ANY OTHER LIABILITY IN CONNECTION WITH THE SALE OF OUR PRODUCTS.