

Technical Data

Distributed by KPR Adcor Inc. USA & Canada www.corrosionvci.com Toll free: 1-866-577-2326

Tel: 905-628-3232 E-mail: kpr@corrosionvci.com


Fax: 1-905-628-2529

Versil-Pak 4 Flexible, Greaseproof, Waterproof Barrier Material

Product Description

Versil-Pak 4 is a protective packaging material that combines a highly formulated adhesion wax and a polyester film with a heavy mesh cotton fabric. The wax and polyester film provide barrier properties while the fabric allows ease of handling. It is especially suited for hand wrap applications in the field.

Versil-Pak provides corrosion, abrasion and impact protection. Standard size rolls are 36" x 50 yds. and 36"x 100 yards. Other sizes are available upon request.



Applications

Versil-Pak protects industrial plant piping where corrosive action is prevalent or where conditions are extremely severe. This includes air lines, sprinkling system piping, cold water pipe, gas pipe, and all other metal tubes.


Construction

Heavy mesh cotton fabric core provides highstrength and carrier of the protective wax.

High adhesion wax assure excellent barrier and is treated with fungicides to help reduce antimicrobial induced corrosion (MIC).

Polyester film increases barrier properties over those without.

Optional: VCI (volatile corrosion inhibitors) provide additional corrosion protection performance. Refer to Nox-Rust® VCI Versil-Pak 4).



Benefits

- Less bulky and more efficient coverage than other petroleum wraps.
- ° Conforms to odd shapes and sizes.
- ° Barrier to contaminants even in most demanding conditions.
- ° Heavyweight mesh provides high tear strength.

Versil-Pak 4 Page 2

Physical Properties

Typical values and are not to be construed as specifications. If specifications are required, please discuss with your sales representative.

<u>Typical Physical Test Results</u> Weight, lbs./Sq.Yd.	Typical Values 0.53	TAPPI Test Method T-410
Thickness, mils.	13	T-411
Tensile Strength, lbs./in. Machine Direction Cross Machine Direction	20 16	T-404
Bursting Strength, psi	61	T-403
Tear Strength, Elmendorf, gms Machine Direction Cross Machine Direction	600 900	T-414

Shelf Life 5 Years from date of shipping

This shelf life statement is only valid for product stored in the original shipping container used by Daubert Cromwell or equivalent and not at high temperatures. Storage outside these conditions voids this statement.

Rev. 7/08 JMB

The data, statements and recommendations in this product WARRANTY - All products manufactured by us are information sheet are based on testing, research and other development work, which has been carefully conducted by us, and we believe such data, statements and recommendations will serve as reliable guidelines. Physical properties shown above represent typical values and are not intended for use in writing specifications. However, this product is subject to numerous uses under varying conditions over which we have no control, and accordingly, we do NOT warrant that this product is suitable for any particular use. Users are advised to test the product in advance to make certain it is suitable for their particular production conditions and use.

warranted to be first class material and free from defects in material and workmanship.

Liability under this warranty is limited to the net purchase price of any such products proven defective or, at our option, to the repair or replacement of said products upon their return to us transportation prepaid. All claims on defective products must be made in writing within 30 days after the receipt of such products in your plant and prior to further processing or combining with other material and products.

WE MAKE NO WARRANTY, EXPRESS OR IMPLIED, AS TO THE SUITABILITY OF ANY OF OUR PRODUCTS FOR ANY PARTICULAR USE, AND WE SHALL NOT BE SUBJECT TO LIABILITY FROM ANY DAMAGES RESULTING FROM THEIR USE IN OPERATIONS NOT UNDER OUR DIRECT CONTROL.

THIS WARRANTY IS EXCLUSIVE OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, AND NO REPRESENTATIVE OF OURS OR ANY OTHER PERSON IS AUTHORIZED TO ASSUME FOR US ANY OTHER LIABILITY IN CONNECTION WITH THE SALE OF OUR PRODUCTS.